

FLUXO 5

Remover for White Contrast Paint - Magnetic Particle Inspection

General Appearance & Composition

- Remover for White Contrast Paint
- Processing Temperature: 0 °C to 50 °C
- **FLUXO 5** is a mixture of solvents.
- Fast drying
- Associated products:
 - Black Ink: **FLUXO 3 / FLUXO 215**
 - White Contrast Paint: **FLUXO 4 / FLUXO 7**
- Manufacturer: SREM TECHNOLOGIES

Approval & Specifications

- EN ISO 9934-2
- ASTM E1444 - Section 5.8
- ASME BOILER AND PRESSURE VESSEL CODE, SECTION V
- Code RCC-M - Tome III
- ASTM E709
- Low in Sulphur & Halogens (Nuclear Quality)

Properties

- Flash Point: < 0 °C
- Aspect : Colourless liquid
- Mechanic stability: stable product
- Stability in time: minimum 60 months
- Density: 810 g.cm⁻³ (20 °C)

Application

- Remove tinder, rust and other contaminations from surface.
- For a good contrast: spray a thin film of **FLUXO** White Contrast Paint on the surface of the part.
- During magnetization spray **FLUXO 3 / FLUXO 215** on the surface.
- Defects will appear as black magnetic particle indications under daylight.
- After control the surface can be cleaned with **FLUXO 5** Paint Remover.

Shelf Life

- Minimum of 5 years. stored at room temperature.
- Please refer to the Safety Data Sheet

Pack Sizes

- Aerosol Can 500mL
- Drum 5L

